



# Steel 1.0503

## Alternative Designations

Standard	AFNOR	ANSI/AA	UNS	JIS	SIS	UNE
Designation	AF65C45	1045	G10450	S45C	1650	C45K

## Details

This material has low thermal conductivity and low ductility among wrought carbon steels. With a relatively high tensile strength of 630MPa, it is used for screws, forgings, drills, shafts etc. A combination of size accuracy, straightness and concentricity results in minimal wear in high speed applications.

## Key Features

High tensile strength • low ductility • Low thermal conductivity

## Chemical Composition

Element	C	Si	Mn	P	S	Cr	Mo	Ni
Percentage	0.45	0.4	0.5 – 0.8	0.03	0.02 – 0.035	0.4	0.1	0.4

## Mechanical Properties

Property	Yield strength [MPa]	Ultimate tensile strength [MPa]	Elongation [%]	Hardness
Value	275	560	16	255



## Physical Properties

Property	Value
Density [g/cm <sup>3</sup> ]	<b>7.85</b>
Module of elasticity [GPa]	<b>543</b>
Electrical conductivity [m/Ω · mm <sup>2</sup> ]	<b>4.76</b>
Coefficient of thermal expansion [K <sup>-1</sup> · 10 <sup>-6</sup> ]	<b>12</b>
Thermal conductivity [W/m · K]	<b>34.2</b>
Specific heat capacity [J/kg · K]	<b>332</b>

